



Thorndike Corporation

680 North Bedford Street
East Bridgewater, MA 02333
(508) 378-9797 / 9798
Fax: (508) 378-1529
Toll free: 800-367-3367
www.thorndikecorp.com

Bulletin No.: 111-2800

Updated 10.23.1997

Material: TC2800

MATERIAL CHARACTERISTICS

Test Frequency:	10.0 GHz
Attenuation:	>62.6 dB / cm at 10 GHz >9.8 dB / cm at 3 GHz
Relative Permeability:	2.30
Relative Permittivity:	16.5 with a 5% tolerance
Loss Factor dB/inch:	159
Resistivity:	>10E12 ohm cm
Thermal Expansion:	30 x 10E-6 per degrees C.
Outgassing Characteristics:	See note 1 below
Color:	Brown to Black
Dielectric Strength:	>380 kv/in
Operating Temperature Range:	to 500 degrees F.
Tensile Strength:	>7500 psi
Water Absorption:	<0.05% (20 days @ 25 deg. C.)
Machinability:	Excellent

Note 1:

NASA CRITERIA FOR SPACE MATERIAL ACCEPTANCE

- TML less than or equal to 1.0%
- CVCM less than or equal to 0.10%

Outgassing characteristics:

- 24 hr period at 125 deg. C. Vacuum of 10E-6 torr total weight loss, .238%
- Volatile condensable materials 0.008% on sample 1-3/16 x .060 in. thick

CALL THORNDIKE CORPORATION FOR ALL YOUR LOW AND HIGH POWER ABSORBER REQUIREMENTS!!!

